

SPCRYL 60 ECO & SPCRYL 61

Description

SPCRYL 60 ECO is a mid molecular weight resin solution of SPCRYL MOFG for water-based overprint varnishes and inks

Key features & Benefits

- Broad range utility
- Balance of Gloss & Dispersion
- Very low VOC solution

Physical Properties SPCRYL 60 ECO

-Appearance:	Clear Solution
-Non-Volatile %	34
-pH (30°C)	8.4
-Viscosity, (cps 30°C)	5500
-Molecular Weight, (Mw)	8,500 GPC
-Acid Number(mg KOH/gm)	215
-Glass Transition temperature (Tg)	85°C DSC

Description

SPCRYL 61 is a customized mid molecular weight resin solution of SPCRYL MOFG for water-based overprint varnishes and inks

Key features & Benefits

- Broad range utility
- Balance of Gloss & Dispersion
- Very low VOC solution

Physical Properties SPCRYL 61

-Appearance:	Clear Solution
-Non-Volatile %	34
-pH (30°C)	8.4
-Viscosity, (cps 30°C)	5200
-Molecular Weight, (Mw)	8,500 GPC
-Acid Number(mg KOH/gm)	215
-Glass Transition temperature (Tg)	85°C DSC



Safety

When handling these products, advice and information given in the safety data sheet must be complied with. Further, protective and workplace hygiene measures adequate for handling chemicals must be observed.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.